

112.22

SHERWIN-WILLIAMS®

C-77

SHRINK-FREE SPACKLING



**SHERWIN
WILLIAMS.**

PRODUCT DESCRIPTION

A lightweight, fast drying spackle formulated not to shrink or crack, even on large surface repairs. Use to fill drywall joints, nail indentations, cracks and openings around windows, doors and molding.

- Will not shrink
- Water clean-up
- Indoor/outdoor use
- Paintable

COLOR AVAILABILITY

Color	SMIS Number	Size
White	151 -0627	1/2 Pint
White	151-0619	Quart
White	151 -0817	Gallon

Properties

Color:	White
Dry Time:	30 - 120 Minutes (size dependent)
Base:	Acrylic Emulsion
Viscosity:	Smooth paste
Weight/Gallon:	3.5 - 4.0 lbs.
Volatile:	Water

112.22

SHERWIN-WILLIAMS®

C-77

SHRINK-FREE SPACKLING



PREPARATION & USE

Surface must be clean, dry, dirt and dust free, and free from loose plaster, grease or wax. Remove loose paint. Roughen smooth surfaces with sandpaper.

APPLICATION: Stir C-77 Compound thoroughly. If compound appears dry, add one teaspoon of water for each 8 oz. of Spackling. Fill cracks or dents with putty knife. Force spackle into repair with slight excess overlapping edges of repair. Let dry 1/2 to 2 hours depending on size of repair. Sand with fine or medium sand paper or sanding block. Dents less than 1/16" deep can be painted over almost immediately.

PRIMING: For best results, it is always recommended to prime Sherwin-Williams C-77 Compound prior to topcoating with paint. To prevent flashing, prime entire surface (ceiling, walls, door, etc.) with a stain blocking primer prior to finishing coat. Spot priming (patched area only) or no priming at all can result in flashing or reverse flashing (shiners). The primer will aid in the uniformity of the topcoat's appearance. Due to the porosity of some substrates, the entire surface to be painted may require primer for the most uniform appearance of the topcoat.

PAINTING: When dry, Sherwin-Williams C-77 Shrink-Free Lightweight Spackling Compound can be top-coated with most commonly used paint systems.

CLEAN UP: Clean up with water while still wet.

LIMITATIONS

Should not be applied where joint or other movement is expected. C-77 must be dry before painting. Normal dry time is 10 to 60 minutes but can be up to 3 days for deep holes. Skim coating can lead to loss of adhesion, cracking or paint alligating and is not recommended. Filling butt joints is also not recommended. Keep from freezing.

SHELF LIFE: Sherwin-Williams C-77 Shrink-Free Spackling will exhibit a 12 month shelf life from the date of manufacture when stored at room temperature.

PRECAUTIONS

Do not take internally; keep out of the reach of children; close container after each use. May irritate eyes. Immediately flush eyes with plenty of water for at least 10 minutes. Call physician.